



Radhaswami Industries

Refractory Concrete Solutions



9001 : 2015



Decide with Confidence

Technical Specification

MORTARS:

Brand Name RADHASET	Service temp °C	Chemical Analysis		Grading mm
		Al ₂ O ₃ % min	Fe ₂ O ₃ % min	
RS-50 NORMAL	1550	50	4.0	0-1.5
RS-50 FINE	1550	50	4.0	0-0.5

PASTE

RADHATEX	
Service Temperature	1600°C
P.C.E Orton Cone	33
Density	2200 kg/m ³
Initial Setting Time	2 hours
Final Setting Time	6-8 hours
Grain Size	0-0.5 mm
Al ₂ O ₃	40-45%
SiO ₂	50-55%
Fe ₂ O ₃	2%

RADHATEX is high temperature air setting refractory cement supplied in air tight drums in ready to use paste form

physical tests as per BIS 10570 , chemical analysis as per BIS 12107. Figures shown are for vibratory cast materials only.

No. 266, GIDC Estate, Waghodia, GIDC Estate, Waghodia, Vadodara-391760, Gujarat, India, +91 98240 66136, 02668 263 036

radharefcast@yahoo.co.in, info@radhaswamiindustries.com

www.radhaswamiindustries.com